

Confidential Report

Our Ref: 26/02454C/09/18



Notified Body for PPE Directive, Construction Products Regulation & Marine Equipment Directive I.D. No. 0338 & 0339



Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 1 of 8

Client:	Kleen-Tex Industries Limited
	Cobden Mill Industrial Estate
	Emlyn Street
	Farnworth
	Rolton

Job Title: Fire Test on One Sample of Mat

Client's Order No: --

Date of Receipt: 03 September 2018

Description of Sample(s): One sample of mat, reference; Concourse 7mm

BL4 7EB

Work Requested: We were asked to make the following test(s):

BS EN 13501-1

Note: This report relates only to the samples submitted and as described in the report.

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited





1066



Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 2 of 8

Client: Kleen-Tex Industries Limited

FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2010 Reaction to fire tests for building products – Part 2: Ignitability when subjected to direct impingement of flame

Date of Test: 24/09/2018

Conditioning

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

Procedure

The sample was tested in accordance with BS EN ISO 11925-2:2010.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

- 1. If ignition occurs
- 2. Presence of flaming debris, if applicable
- 3. Ignition of the filter paper, if applicable

Duration of test

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 3 of 8

Client: Kleen-Tex Industries Limited

Classification Criteria

The samples were classified according to BS EN 13501-1:2007 + A1:2009 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification			
Classification Criteria (mean values)			
E _{FL}	Fs ≤ 150mm within 20 seconds		
F _{FL}	None (No performance determined)		

Flaming droplets / particles classification			
Classification Criteria			
No classification	Pass		
d2	Fail (Ignition of paper)		

Results

Specimen			Tip of flame re	eaches 150mm	Flaming droplets		
		Ignition (Yes or No)	Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)	
Machine Direction	1	Yes	No	N/A	No	No	
	2	Yes	No	N/A	No	No	
	3	Yes	No	N/A	No	No	
Across Machine Direction	1	Yes	No	N/A	No	No	
	2	No	No	N/A	No	No	
	3	No	No	N/A	No	No	





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 4 of 8

Client: Kleen-Tex Industries Limited

FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010 Indicative (***) Reaction to fire tests for Floorings - Part 1: Determination of the burning

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 24/09/2018

Conditioning

The specimen was conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m^3 representing the standard substrate of Class A1fl or A2fl.

Procedure

The test was carried out in accordance with BS EN ISO 9239-1. The sponsor sampled and cut the specimen to the dimensions stated.

The specimen was individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11 kW/m² to 1 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 5 of 8

Client: Kleen-Tex Industries Limited

Classification Criteria

The sample was classified according to BS EN 13501: BS EN 13501-1:2007 + A1:2009 Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For Floorings including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m²)				
B _{fl}	8.0				
C _{fl}	4.5				
D _{fl}	3.0				
	Smoke Production % x min				
s1	≤ 750				
s2	Not s1				

When tested to BS EN ISO 11925-2:2010 the sample has to have a flame spread (Fs) of: Fs \leq 150mm within 20 seconds (Class Efl)

Results

The test results relate to the behaviour of the test specimen of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 6 of 8

Client: Kleen-Tex Industries Limited

Results (Continued)

<u>Specimen</u> <u>No.</u>	<u>Direction of</u> <u>specimen</u>	Smoke Ob Max %	scuration <u>% x min</u>	Maximum Flame front (mm)	Critical Heat Flux (kW/m²)	<u>Duration of</u> <u>Flaming (sec)</u>	
1	Across	98	1463	460	4.5	1800 ME	
2 ME=Manually Extinguished	Machine	100	1807	710	1.9	1800 ME	
<u>Distance</u>		Time for each specimen to burn (s)					
<u>Burnt (mm)</u>		<u>1</u> <u>2</u>					
50		151 152					
100		247 217					
15	0	331 272					
20	0	473 332					
25	0	540		393			
30	0	628		506			
35	0	753	558				
40	0	995	995 608				
450	0	1507 715		715			
50	500				800		
550				908			
600					1043		
650				1411			
70	0				1620		

Note

Only two specimen was tested. Results of 3 specimens in the same direction are used to determine an absolute class.

The specimen of floor covering was tested stuck down onto a 6mm fibre cement board as defined in BS EN 13238:2001 using Stycobond F41 Adhesive.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 7 of 8

Client: Kleen-Tex Industries Limited

Comments

In our opinion, based on the tests carried out on the sample supplied;

- a) the results of the BS EN ISO 11925-2:2002 test indicate the sample meets the requirements of a Class E_{FL} . It should be noted that this is only class that can be achieved when tested to this method alone.
- b) the results of the BS EN ISO 9239-1:2002 test indicate the sample is unclassifiable when tested to this method alone. Therefore, the test was terminated after one specimen.

Conclusion

In our opinion, the results indicate that the sample when classified to BS EN 13501-1:2002 meets an overall classification of: **Class E**_{fl}.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by: P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 25 September 2018

Our Ref: 26/02454C/09/18

Your Ref:

Page: 8 of 8

Client: Kleen-Tex Industries Limited

Uncertainty Budget - Annex

The uncertainty budget for BS EN 13501-1:2002 was determined as follows:-

Overall (BS EN ISO 9239-2)

The uncertainty varies, therefore:

At position between a Euroclass B to C \pm 15% At position between a Euroclass C to D \pm 15.5% At position between a Euroclass D to E \pm 17.5%

