



Kleen-Tex Polska Sp. z o.o.  
ul. Fabryczna 5/12  
26-130 Suchedniów  
Poland

**Your Reference**  
**Customer Number** 60564  
**Contact Person** Barcik Roman  
**E-Mail** rbarcik@kleen-tex.pl

Vienna / 20.05.2021 / atad

## Test Report VN720 184857.1

### Application

Determination of the static electrical propensity according to ISO 6356.

### Test Material

"Water-Horse" , "Super-Mat"

The test material used for testing was made anonymous for laboratory purposes.  
A detailed sample list is included in the document.

### Issuing

Original Issuing, 20.05.2021  
Number Of Included Pages: 4

### OETI - Institute for Ecology, Technology and Innovation GmbH

**Ing. Hannes Vittek**

Manager Flooring Technology & Interior Design



OETI - Institut fuer Oekologie, Technik und Innovation GmbH | Siebenhirtenstrasse 12A, Objekt 8, 1230 Vienna, Austria  
tel +43 1 5442543-0 | e-mail office@oeti.biz | www.oeti.biz | FN 326826 b | VAT No. ATU65149029 | EORI ATEOS1000015903  
Raiffeisenlandesbank Niederösterreich-Wien AG | IBAN AT723200000013108725 | BIC RLNWATWW  
UniCredit Bank Austria AG | IBAN AT941200023410378800 | BIC BKAUATWW

Es gelten ausschließlich unsere Allgemeinen Geschäftsbedingungen | Only our general terms and conditions apply

Member of TESTEX Group



## 1 Application

Date of Order	Scope of Order
22.04.2021	Description Of Specimen - Textile Floor Coverings - EN 1307 Static Electrical Propensity - Walking Test - ISO 6356

## 2 Samples

No.	Receipt	Sample Identification
1	26.04.2021	"Water-Horse"
2	26.04.2021	"Super-Mat"

(Unless otherwise stated samples are provided by the customer.)

## 3 Tests Performed / Results

#1  
"Water-Horse"

#2  
"Super-Mat"

Description Of Specimen - Textile Floor Coverings EN 1307 *	#1 "Water-Horse"	#2 "Super-Mat"
<ul style="list-style-type: none"> <li>• Manufacturing procedure</li> <li>• Structure of face side</li> <li>• Primary backing</li> <li>• Colouration of the surface</li> <li>• Type of backing</li> <li>• Type of fibres at face side</li> <li>• Dimensions</li> <li>• Description according to standard</li> </ul>	<p style="text-align: center;">Tufted Structured Non-woven fabric Multicolored unpatterned Nitrile rubber 100% Polypropylene Mat Pile carpet</p>	<p style="text-align: center;">Tufted Cut pile Non-woven fabric Multicolored unpatterned Nitrile rubber 100% Polyamide Mat Pile carpet</p>



	#1 "Water-Horse"	#2 "Super-Mat"
<b>Static Electrical Propensity - Walking Test</b>		
ISO 6356		
• Testing climate		
Temperature	[°C]	23
Air humidity	[%]	25
• Underlay		
insulating rubber mat		
XS-664P Neolite		
• Pretreatment		
none		
• Body-Voltage supplied condition		
1. Measurement	[kV]	- 0,5
2. Measurement	[kV]	- 0,4
3. Measurement	[kV]	+ 0,5
Mean value	[kV]	+ 0,4
• <b>Assessment according to EN 14041:2007</b>		
<b>antistatic</b>		<b>antistatic</b>

## 4 Remarks

### Period of Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or OETI. The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product is produced unchanged. Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

### Sample Material

Results of performed tests only refer to the sample material provided. Without explicit written other agreement testing is destructive and the sample material is transferred to the property of OETI, which is entitled to freely decide on storage and disposal.

### Issuing

This test report is only issued as a PDF. Translations will be marked accordingly on the cover sheet.

### Quality Management, Accreditation And Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025. OETI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body (NB0534). (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation was provided by Akkreditierung Austria. The scope of accreditation is listed on [www.oeti.biz](http://www.oeti.biz). Due to the system for the mutual recognition of national accreditations (ILAC/IAF), this accreditation is valid worldwide.

Statements of conformity are based on the specifications of the specified standard. The "simple acceptance rule" applies, that means the measurement uncertainty is stated for the statement of conformity, but not taken into account.

In this report individual non-accredited test procedures are marked with \*. Nevertheless, the analysis was also carried out for these parameters at the same level of quality as for the accredited parameters.

According to the decree on the use of the accreditation mark ("AkkZV") the accredited Conformity Assessment Body is the only one to use the accreditation mark. Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of Regulation (EU) 2016/425 have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

### Copyright And Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents. Reports are protected under international copyright laws. Written consent of the OETI GmbH is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of Report